

**MS Word Export To Multiple PDF Files Software - Please purchase
license. SECTION 1
1.2 Results Summary
Art and Education**

ACM SURVEY RESULTS

The following homogeneous building material types were sampled as part of this survey conducted May 20-21, 2003. Results are summarized in the table below:

1st Floor

MTL #	MATERIAL DESCRIPTION	LOCATION	F/NF ¹	COND. ²	% ACM	# SAMP.	QUANTITY
01	Drywall (white) Joint compound*	SE entry, 107a, 108, 109, 109a, 111, 111c, 114, 118, 121, 127, 127a, 127b, 143a, 145, 160a, 160b, 160c, 168, 168a, 169, 175, 175a, 176, 183, 186, 191, 192, 194, 1206, 1206a, 1206b, 1207, 1211, 1211a, 1231, 1231b, 1232, 1233, 1233a, 1233b, 1233c	F	Good	Drywall = ND JC = ND	3	N/A
02	9" x 9" Gray floor tile/ mastic	Hallways, 193, 192, 186, 191, 183, 177, 175a, 175, 160a, 160b, 160c, 1206b, 1233, 1233b, 1233c, 1232, 1215, 1215a, 1211, 1211a, 1207, 106, 118, 120, 127, 127a, 127b, 140, 143a, 153, 145, 142a, 142b	NF	Good	Floor tile = 5% Mastic = 5%	3	14,000 SF
03	Pink sink under coating	All floors: 168a, 160c, 1206, 1227, 250a, 239a, 268, 278, 286, 385	NF	Good	4%	3	40 SF

37	Tan cove base/ mastic	Hallway, 246, 246a, 239, 239a and b, 238, 225, 209, 210, 211, 213, 214, 214a, 215, 217, 219, 221, 223, 207, 208, 205, 203, 210, 206, 271, 268, 285, 286, 290	NF	Good	Cove base = ND
----	--------------------------	---	----	------	----------------

62	Drywall (orange) Joint compound*	373e	F	Good	Drywall = ND JC = <1%	3	500 SF
63	Drywall (white) Joint compound*	All rooms except hallways, 392, 392a, b, c, d, e, 373e, 369, 369a, b, WRR, MRR, 311, shops, elevator	F	Good	Drywall = ND JC = <1%	3	20,000 SF
64	1' x 1' White fissure ceiling panel	384, 384a, 382, 382a, 378, 368a, b, c, 368, 366, 366a, 307, 309, 311, 313, 315, 317	F	Good	ND	3	N/A
65	Brown mastic behind ceiling panel	Same as above (MTL #64)	NF	Good	ND	3	N/A
66	Drywall (blue) Joint compound*	392, 392a thru e	F	Good	Drywall = ND JC = <1%	3	3,500 SF
67	2' x 2' White fissure ceiling panel	392, 392c	F	Good	ND	3	N/A